



Technical Evaluation Report™

A Duly Authenticated Report from an Approved Agency

Report Number 1808-03

ThermoPLY® Red and ThermoPLY® Red AMG Structural Sheathing - Canada

Amrize Building Envelope, LLC

Product:

ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing

Issue Date: November 19, 2018

Revision Date: November 5, 2025

Subject to Renewal: April 1, 2026



Use the QR code to access the most recent version or a sealed copy of this report at dricertification.org.





Company Information:

Additional Listees:

Amrize Building Envelope, LLC 26 Century Blvd Ste 205 Nashville, TN 37214-4601

Phone: 989-798-5923

Website: www.oxengineeredproducts.com

OX Engineered Products, LLC 700 Centreville St Constantine, MI 49042-1273 Phone: 269-435-2425

CSI Designations:

DIVISION: 06 00 00 - WOOD, PLASTICS AND COMPOSITES **DIVISION**: 07 00 00 - THERMAL AND MOISTURE PROTECTION

Section: 06 12 00 - Structural Panels Section: 07 25 00 - Water-Resistive Barriers/Weather Barriers

Section: 07 27 00 - Air Barriers

Section: 06 12 19 - Shear Wall Panels Section: 06 16 00 - Sheathing

1 Innovative Products Evaluated¹

1.1 ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing

2 Applicable Codes and Standards²

- 2.1 Codes
 - 2.1.1 NBC—10, 15, 20: National Building Code of Canada
 - 2.1.2 NECB—17, 20: National Energy Code of Canada for Buildings
- 2.2 Standards and Referenced Documents
 - 2.2.1 ASTM E72: Standard Test Methods of Conducting Strength Tests of Panels for Building Construction
 - 2.2.2 ASTM E283: Standard Test Method for Determining Rate of Air Leakage Through Exterior Windows, Curtain Walls, and Doors Under Specified Pressure Differences Across the Specimen
 - 2.2.3 ASTM E330: Standard Test Method for Structural Performance of Exterior Windows, Doors, Skylights, and Curtain Walls by Uniform Static Air Pressure Difference
 - 2.2.4 ASTM E331: Standard Test Method for Water Penetration of Exterior Windows, Skylights, Doors, and Curtain Walls by Uniform Static Air Pressure Difference
 - 2.2.5 ASTM E564: Standard Practice for Static Load Test for Shear Resistance of Framed Walls for Buildings
 - 2.2.6 ASTM E2126: Standard Test Methods for Cyclic (Reversed) Load Test for Shear Resistance of Vertical Elements of the Lateral Force Resisting Systems for Buildings
 - 2.2.7 CAN/ULC-S102: Standard Method of Test for Surface Burning Characteristics of building Materials and Assemblies
 - 2.2.8 CSA O86: Engineering Design in Wood
 - 2.2.9 CWC: Engineering Guide for Wood Frame Constructionist

3 Performance Evaluation

- 3.1 Testing and related engineering evaluations are defined as intellectual property and/or trade secrets.3
- 3.2 Engineering evaluations are conducted within DrJ's ANAB accredited ICS code scope, which are also its areas of professional engineering competence.⁴





- 3.3 ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing have been evaluated to determine:
 - 3.3.1 Structural performance under lateral load conditions (wind and seismic) in accordance with NBC Division B Subsection 9.23.13 and Subsection 4.1.8.
 - 3.3.1.1 **Table 2** provides Seismic Design Coefficients (SDC) that conform to the requirements in NBC Division B Subsection 4.1.8 for design of wall assemblies in buildings that require seismic design in accordance with NBC (i.e., all seismic design categories).
 - 3.3.1.2 The basis for equivalency testing is outlined in Sentence 4.1.8.9.(5) of NBC:

If it can be demonstrated through testing, research and analysis that the seismic performance of a structural system is at least equivalent to one of the types of SFRS mentioned in Table 4.1.8.9., then such structural system will qualify for values of Rd and Ro corresponding to the equivalent type in that Table. (See Note A-4.1.8.9.(5).)

- 3.3.2 Structural performance under transverse loads for use to resist factored external wind loads in accordance with NBC Division B Subsection 4.1.7.
- 3.3.3 Structural performance under uplift and gravity loads for use with single top plates when constructed in accordance with NBC Division B Article 9.23.11.3.
- 3.3.4 Performance for use as a Water-Resistive Barrier (WRB) in accordance with NBC Division B Note A-5.6.2.1.
- 3.3.5 Performance for use as an air barrier material in accordance with NBC Division B Article 9.36.2.10.
- 3.3.6 Performance for surface burning characteristics in accordance with NBC Division B Subsection 3.1.12 and Article 9.10.3.2.
- 3.4 Any regulation specific issues not addressed in this section are outside the scope of this report.

4 Product Description and Materials

4.1 ThermoPLY Red Structural Sheathing, evaluated in this report, is shown in Figure 1.




Figure 1. ThermoPLY Red Structural Sheathing and Logo





- 4.2 ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing are composed of pressure-laminated plies consisting of high strength cellulosic fibers. These fibers are specially treated to be water resistant and are bonded with a proprietary water resistive adhesive. A protective polymer layer is applied on both sides of the panel, and additionally, foil facings may be applied on one or both faces.
 - 4.2.1 ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing panels have a nominal thickness of 2.9 mm (0.113") and nominal weight of 2.02 kg/m² (0.414 lb per square foot).
- 4.3 Material Availability
 - 4.3.1 Standard Widths:
 - 4.3.1.1 1,219 mm (48")
 - 4.3.1.2 1,238 mm (48³/₄")
 - 4.3.2 Standard Lengths:
 - 4.3.2.1 2,438 mm (96")
 - 4.3.2.2 2,743 mm (108")
 - 4.3.2.3 3,048 mm (120")
 - 4.3.3 Custom widths and lengths can be manufactured.

5 Applications

- 5.1 General
 - 5.1.1 ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing panels may be used in the following applications as:
 - 5.1.1.1 Wall sheathing in buildings constructed in accordance with NBC Division B Section 9.23 for wood frame construction.
 - 5.1.1.2 Structural wall sheathing to provide lateral load resistance (wind and seismic) for braced wall panels used in light-frame wood construction.
 - 5.1.1.3 Structural wall sheathing to provide resistance to transverse loads for wall assemblies used in light-frame wood construction.
 - 5.1.1.4 Structural wall sheathing to provide resistance to uplift loads for wall assemblies used in light-frame wood construction.
 - 5.1.1.5 An approved alternative WRB when installed in accordance with Section 5.3 and Section 6.
 - 5.1.1.6 An approved air barrier material when installed in accordance with **Section 5.4** and **Section 6**.
- 5.2 Structural Applications
 - 5.2.1 General Structural Provisions:
 - 5.2.1.1 Except as otherwise described in this report, ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing shall be installed in accordance with the applicable building codes listed in **Section 2**, using the provisions set forth herein for the design and installation of Wood Structural Panels (WSP).
 - 5.2.1.1.1 ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing are permitted to be designed in accordance with NBC Division B Part 9 Article 9.23.13.1, Article 9.23.13.2, and Article 9.23.13.3 for the design of lateral-load-resisting systems using the methods and conditions set forth therein.





- 5.2.1.2 Anchorage for in-plane shear shall be provided to transfer the induced shear force into and out of each shear wall in accordance with NBC Division B Subsection 9.23.6.
- 5.2.1.3 The maximum aspect ratio for ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing shall be 4:1.
 - 5.2.1.3.1 The minimum full-height panel width shall be 610 mm (24").
- 5.2.1.4 Installation is permitted for single top plate or double top plate applications.
- 5.2.2 Performance-Based Wood-Framed Construction:
 - 5.2.2.1 ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing panels used in wall assemblies designed as shear walls are permitted to be designed in accordance with the methodology used in CAN/CSA-O86 for WSP using the capacities shown in **Table 1**, **Table 2**, and **Table 3**.
 - 5.2.2.2 ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing shear walls are permitted to resist horizontal wind load forces using the specified shear strengths set forth in **Table 1**.
 - 5.2.2.3 ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing shear walls that require seismic design in accordance with NBC Division B Subsection 4.1.8 shall use the seismic specified shear strengths set forth in **Table 2**.
 - 5.2.2.3.1 The ductility response modification factor, R_d, and overstrength-related force modification factor, R_o, as indicated in **Table 2**, shall be used to determine the base shear, element design forces, and design story drift in accordance with NBC Division B Subsection 4.1.8.
 - 5.2.2.4 ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing panels are permitted to resist uplift load forces using the factored uplift loads set forth in **Table 3**.
 - 5.2.2.5 ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing panels are permitted to resist transverse wind load forces using the specified transverse loads as shown in **Table 4**.





Table 1. ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing
- Specified Shear Capacity for Limit States Design – Wind^{1,4}

Product	Joint Condition ³	Maximum Stud Spacing mm (in)	Gypsum Wallboard (GWB) ²	Gypsum Wallboard Fastener Spacing (edge/field) mm (in)	Specified Shear Strength kN/m (plf)
	Lapped or Butted	406 (16) o.c.	12.7 mm (¹ / ₂ ") GWB	102/406 (4/16)	10.2 (700)
				203/203 (8/8)	8.6 (585)
				203/406 (8/16)	8.2 (560)
ThermoPLY Red				406/406 (16/16)	7.1 (485)
Structural Sheathing		610 (24) o.c.		203/203 (8/8)	8.4 (575)
and ThermoPLY Red AMG Structural				406/406 (16/16)	7.0 (480)
Sheathing	Lapped	406 (16) o.c.			6.2 (420)
		610 (24) o.c.	No CWD		5.7 (390)
	Butted	406 (16) o.c.	No GWB	-	5.8 (395)
		610 (24) o.c.			5.3 (360)

SI: 25.4 mm = 1 in, 1 kN/m = 737.6 lb/ft

- Gypsum attached with minimum #6 type W or S screws 32 mm (1¹/₄") long with a minimum edge distance of 9.5 mm (3/₈").
- 3. Where lapped joints are used, the panels shall be overlapped nominally 19 mm ($\frac{3}{4}$ ").
- 4. Straight-line interpolations between fastening patterns are acceptable.

^{1.} ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing attached with staples of minimum 16-gauge, 24 mm (15/16") crown. Staples shall penetrate a minimum of 25.4 mm (1") into the stud. Fasteners are to be installed with the crown parallel to the framing and spaced a maximum of 76 mm (3") o.c. at the panel edges and 76 mm (3") o.c. in the field. Fastener edge distance shall be a minimum 9.5 mm (3/8"). Fastener head shall be in contact with the ThermoPLY surface. Roofing nails (minimum 3 mm [0.120"] x 32 mm [11/4"] with a 9.5 mm [3/8"] head) are a permitted alternative fastener.





Table 2. Limit States Design - Seismic Performance of ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing 1,3,7

Seismic	Joint V	Gypsum ^{2,10} Wallboard (edge/field) mm (in)		Stud Shear Spacing Strength mm kN/m	Ductility Factor, R _d ^{5,6}	Overstrength Force Modification Factor, R _o 6	Structural System Limitations and Building Height Limit ⁸ m (ft)				
Force- Resisting System			Spacing				I _E F _a S _a (0.2)			I _E F _a S _a (1.0)	
(SFRS)							< 0.2	≥ 0.2 to < 0.35	≥ 0.35 to ≤ 0.75	> 0.75	> 0.3
Light-Frame (Wood) Walls Sheathed with	Lapped or Butted	12.7 mm Gypsum- Fasteners Spaced 203/203	406 (16) o.c.	8.6 (585)	2.0	1.7	NL	NL	20 (65.6)	20 (65.6)	20 (65.6)
ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing	Lapped	15.9 mm Gypsum- Fasteners Spaced 406/406	610 (24) o.c.	7.0 (480)	2.0	1.7	NL	NL	20 (65.6)	20 (65.6)	20 (65.6)
	Lapped or Butted	No GWB	406 (16) o.c.	5.8 (395)	3.0	1.7	NL	NL	30 (98.4)	20 (65.6)	20 (65.6)

SI: 25.4 mm = 1 in, 1 kN/m = 737.6 lb/ft

- 1. ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing attached with staples of minimum 16-gauge, 24 mm (15/16") crown. Staples shall penetrate a minimum of 25.4 mm (1") into the stud. Fasteners are to be installed with the crown parallel to the framing and spaced a maximum of 76 mm (3") o.c. at the panel edges and 76 mm (3") o.c. in the field. Fastener edge distance shall be a minimum 9.5 mm (3/8"). Fastener head shall be in contact with the ThermoPLY surface. Roofing nails (minimum 3 mm [0.120"] x 32 mm [11/4"] with a 9.5 mm [3/8"] head) are a permitted alternative fastener.
- 5. Gypsum attached with minimum #6 type W or S screws 32 mm (11/4") long with a minimum edge distance of 9.5 mm (3/8").
- 6. All seismic design parameters follow the equivalency as defined in Section 3 of this report.
- 7. Where lapped joints are used, the panels shall be overlapped nominally 19 mm (3/4").
- 8. Response modification coefficient, R_d, for use throughout NBC.
- 9. For combinations of different types of SFRS acting in the same direction in the same story, R_dR_o shall be taken as the lowest value of R_dR_o corresponding to these systems. See NBC Division B Article 4.1.8.9.
- 10. Consider the additional system restrictions in Article 4.1.8.10 of NBC Division B.
- 11. NL = Not Limited. Heights are maximum height limits above grade, as defined in NBC Division B Table 4.1.8.9.
- 12. ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing may be installed with either lapped joints or butted joints.
- 13. NBC Table 9.23.13.6 requires 15.9 mm ($^{5}/_{8}$ ") thick gypsum with framing 610 mm (24") o.c.





Table 3. Limit States Design - Uplift Performance of ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing Single Top Plate¹

Type of ThermoPLY Structural Sheathing	Specified Uplift Capacity kN/m (plf)	Maximum Stud Spacing mm (in)	Fastener Schedule		
ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing Single Top Plate	4.5 (310)	406 (16) o.c.	Minimum 24 mm (15/16") crown, 32 mm (11/4") leg 16-gauge galvanized staples or 3 mm (0.120") x 32 mm (11/4") roofing nails, 76 mm (3") o.c. to perimeter/field		

SI: 25.4 mm = 1 in, 1 kN/m = 737.6 lb/ft

Table 4. Limit States Design - Summary of Specified Pressures for ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing Resisting Transverse Wind Loads^{1,3}

Structural	Transverse Wind Load Resistance			
Sheathing Product	Maximum Stud Spacing mm (in)	Hourly 1-in-50 Wind Pressure ² kPa		
ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing	406 (16) o.c.	8.2		
(2.9 mm)	610 (24) o.c.	6.5		

SI: 25.4 mm = 1 in, 1 kN/m² = 20.9 psf

- 1. Fastener Schedule: Minimum 24 mm (15/16") crown, 32 mm (11/4") leg 16-gauge galvanized staples or 3 mm (0.120") x 32 mm (11/4") roofing nails, 76 mm (3") o.c. to perimeter/field. Staple crowns shall be installed parallel to framing.
- 2. Hourly Wind Pressure (1-in-50) for selected locations can be located in NBC Division B, Appendix C, Table C-2.
- 3. Capacities assume minimum 12.7 mm (1/2") gypsum wallboard installed on the interior side of the wall. Where gypsum wallboard is not installed on the interior side of the wall, a forty percent (40%) reduction in wind pressure resistance shall be applied.

5.3 Water-Resistive Barrier

- 5.3.1 ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing may be used as a WRB as prescribed in with NBC Division B Note A 5.9.4.1.(1), when installed on exterior walls as described in this section.
- 5.3.2 ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing shall be installed with board joints placed directly over exterior framing spaced a maximum of 610 mm (24") o.c. The fasteners used to attach the board shall be installed in accordance with **Section 6**.
- 5.3.3 All seams and joints between boards shall be butt jointed and sealed with an approved construction tape or overlapped in accordance with **Section 6**. Use approved construction tape, such as 73 mm (2⁷/₈") OX SeamTape[®].
- 5.3.4 A separate WRB system may also be provided. If a separate WRB system is used, overlapping or taping of the sheathing joints is not required.
- 5.3.5 Flashing must be installed at all sheathing penetrations and shall comply with all applicable code sections. Approved flashing tapes include Arctic-Flash® Synthetic Flashing, HomeGuard® Flexible Butyl Flashing, and HomeGuard® RA-plus Flashing.

The capacities shown are for the purpose of providing information on the hold-down capacity of the sheathing to the top-plate connection independent of lateral loading. Where combined shear and uplift loading is needed, consult a professional engineer.





5.3.6 Where ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing are used in the intermittent bracing method along a braced wall line, ThermoPLY Green Structural Sheathing may be used as the infill panels between the ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing braced wall panels. In this application, the WRB, air barrier, and transverse load resistance is maintained, provided all seams and joints between boards are overlapped or sealed by the approved construction tape listed in **Section 5.3.3**.

5.4 Air Barrier

5.4.1 ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing may be used as an air barrier material as prescribed in NBC Division B Article 9.36.2.10.

5.5 Fire Safety Performance

- 5.5.1 Surface Burn Characteristics:
 - 5.5.1.1 ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing were evaluated for surface burning characteristics.
 - 5.5.1.2 Flame-spread and smoke developed ratings as shown in **Table 5**, when tested in accordance with CAN/ULC-S102 per NBC Division B Subsection 3.1.12 and Article 9.10.3.2.

Table 5. Surface Burn Characteristics of ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing

Product	Flame Spread	Smoke Developed		
ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing ¹	120	60		
Tested in accordance with CAN/ULC-S102.				

5.6 Non-Structural Applications

- 5.6.1 Where other means of wall bracing are provided or are not required, any grade of ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing may be used to provide other wall functions, when installed in accordance with this section.
 - 5.6.1.1 The sheathing panels are applied to wall framing with minimum 3 mm (0.120") x 32 mm ($1^{1}/_{4}$ ") galvanized roofing nails or 16-gauge galvanized staples having a 24 mm ($1^{15}/_{16}$ ") crown and 32 mm ($1^{11}/_{4}$ ") leg lengths.
 - 5.6.1.2 Fastener spacing shall be a maximum of 152 mm (6") at the edges and 305 mm (12") on intermediate members.
 - 5.6.1.3 Stud spacing shall be a maximum of 610 mm (24") o.c.
 - 5.6.1.4 Minimum fastener penetration into the framing members is 25.4 mm (1").
 - 5.6.1.5 Fasten all staples parallel to the framing member, with an edge spacing of 9.5 mm (3/8") minimum.
 - 5.6.1.6 All panels are vertically or horizontally installed with all joints backed by studs, plates, or blocks when water or air barrier functionality is desired.
- 5.6.2 Incidental tears or penetrations of ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing must be repaired with an approved construction tape. See **Section 5.3.3**.
- 5.6.3 All joints must be installed in one of the following methods:
 - 5.6.3.1 Joints overlap nominally 19 mm $(^{3}/_{4}")$.
 - 5.6.3.2 Butted joints are sealed with approved construction tape. See **Section 5.3.3**.
- 5.7 Where the application falls outside of the performance evaluation, conditions of use and/or installation requirements set forth herein, alternative techniques shall be permitted in accordance with accepted engineering practice and experience. This includes but is not limited to the following areas of engineering: mechanics or materials, structural, building science and fire science.





6 Installation

- 6.1 Installation shall comply with the manufacturer installation instructions, this report, the approved construction documents and the applicable building code.
- 6.2 In the event of a conflict between the manufacturer installation instructions this report and the applicable building code, the more restrictive shall govern.
- 6.3 Installation Procedure
 - 6.3.1 General for Structural and WRB Applications:
 - 6.3.1.1 ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing shall be installed in accordance with the manufacturer installation instructions and this report. Basic instructions are also printed on every ThermoPLY panel.
 - 6.3.1.2 Where the ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing extends beyond the bottom of a wall and overlaps the band joist below, fasten the bottom edge of the ThermoPLY to the wall bottom plate where it meets the band joist. Due to possible shrinkage of the band joist, do not fasten the sheathing to the band joist, or fasten tightly with one fastener every 305 mm (12") to smooth out, if necessary.
 - 6.3.1.3 Where hold-down straps are used, install ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing first, then install the strap over the face of the structural sheathing and attach per the manufacturer installation instructions.

6.3.2 Orientation:

6.3.2.1 ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing may be installed in either the vertical or the horizontal orientation. To be recognized for the structural values listed in this report, or as a water or air barrier, all joints must be backed by studs, plates, or blocks, and fastened.

6.3.3 Fastener Type:

- 6.3.3.1 ThermoPLY Red Structural Sheathing:
 - 6.3.3.1.1 Minimum 3 mm (0.120") x 32 mm (11/4") galvanized roofing nail.
 - 6.3.3.1.2 Minimum 24 mm ($^{15}/_{16}$ ") crown by 32 mm ($^{11}/_4$ ") leg, 16-gauge staples shall be installed per the staple manufacturer instructions.
 - 6.3.3.1.3 Fasteners shall be driven so that the head of the fastener is in contact with the surface of the ThermoPLY Structural Sheathing. Do not overdrive fasteners.

Table 6. Fastener Spacing of ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing

ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing Application	Maximum Panel Edge Fastener Spacing mm (in)	Maximum Panel Intermediate Fastener Spacing mm (in)		
Lateral Shear				
Transverse Loads	76 (3)	76 (3)		
Uplift Loads				
Water-Resistive Barrier	152 (6)	305 (12)		
Air Barrier	152 (6)			
SI: 25.4 mm = 1 in				






- 6.3.3.2 Gypsum Wallboard:
 - 6.3.3.2.1 Where required, gypsum wallboard shall be a minimum 12.7 mm ($^{1}/_{2}$ ") thickness and shall be attached with #6 x 32 mm ($^{1}/_{4}$ ") type W or S screws, diameter 3.3 mm (0.13").
- 6.3.4 Fastener Edge Distance:
 - 6.3.4.1 For NBC Division B Part 9 applications, fastener edge distance is a minimum of 10 mm (0.39") for both ThermoPLY Structural Sheathing and gypsum in accordance with Division B, Article 9.29.5.8 or Division B, Article 9.29.5.9, when installing with nails or screws.
 - 6.3.4.2 Edge distances for staples are specified in the applicable tables in **Section 5**.

6.3.5 Treatment of Joints:

- 6.3.5.1 ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing joints may be either butted or overlapped.
 - 6.3.5.1.1 Lapped joints shall be overlapped by 19 mm (³/₄") nominally and fastened with a single row of fasteners. Always run staples parallel with framing.
 - 6.3.5.1.2 Butt joints shall be placed over framing members and fastened with a single row of fasteners at each panel edge.
- 6.3.6 Window Jamb Adjustments:
 - 6.3.6.1 If windows are made to accommodate traditional 12.7 mm (1/2") sheathing materials, order windows with adjustable nailing fins from the supplier. Door brick moldings may be planed or routed 9 mm (0.35") in order to accommodate the different sheathing thickness, either at the jobsite or by the millwork supplier.
 - 6.3.6.2 ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing must be installed with appropriate flashing and counter flashing in conformance with accepted building standards and in compliance with local building codes and the flashing manufacturer installation instructions.
- 6.3.7 The structural installation procedure shall be in accordance with Figure 2.



STEPS 1 & 2

- 1. Starting at the #1 indicated on the face of the panel, begin fastening from the top of the panel to the bottom. (Refer to installation instructions on the front side of the panel for proper fastener spacing.)
- 2. Moving across the panel, attach fasteners at the top and bottom of the panel until you reach #2 (the next stud). It is important when using staples to fasten them in a parallel direction to the stud.

Figure 2. Installation Instructions – WRB Installation Procedure





- 6.3.7.1 Overlapped Joint Install the first panel per **Figure 2**.
 - 6.3.7.1.1 Overlap the next panel 19 mm $(^{3}/_{4}")$ over the first panel, and fasten the joint with a common line of fasteners.
 - 6.3.7.1.2 For ThermoPLY Red AMG Structural Sheathing, ensure the panel is properly positioned on the wall prior to removal of the adhesive release liners on vertical edges. Fasten the overlapped joint with a common line of fasteners.
- 6.3.7.2 Butted Joint with Flashing Install panels per **Figure 2** with joints butted (no overlap).
- 6.3.7.3 Seal butted seams with approved construction tape (**Section 5.3.3**), after attachment of the wall panels and all fasteners in the wall line.

7 Substantiating Data

- 7.1 Testing has been performed under the supervision of a professional engineer and/or under the requirements of ISO/IEC 17025 as follows:
 - 7.1.1 Transverse load testing in accordance with ASTM E330
 - 7.1.2 Uplift load testing in accordance with ASTM E72
 - 7.1.3 Water penetration testing in accordance with ASTM E331
 - 7.1.4 Test reports and data for determining use as an air barrier in accordance with ASTM E283
 - 7.1.5 Lateral load testing and data for determining comparative equivalency for use as an alternative material in accordance with ASTM E2126
 - 7.1.6 Test reports and data for determining surface burning characteristics in accordance with CAN/ULC S102
 - 7.1.7 Test reports and data for determining comparative equivalency for use as an alternative material in accordance with NBC Division A Section 1.2
- 7.2 Information contained herein is the result of testing and/or data analysis by sources that conform to the evaluation requirements of NBC Volume 1 Relationship of the NBC to Standards Development and Conformity Assessment and/or professional engineering regulations. DrJ relies upon accurate data to perform its ISO/IEC 17065 evaluations.
- 7.3 Where appropriate, DrJ's analysis is based on provisions that have been codified into law through provincial, territorial, or local adoption of codes and standards. The developers of these codes and standards are responsible for the reliability of published content. DrJ analysis may use code-adopted provisions as a control sample. A control sample versus a test sample establishes a product as being equivalent to that prescribed in this code in quality, strength, effectiveness, fire resistance, durability and safety.
- 7.4 The accuracy of the provisions provided herein may be reliant upon the published properties of raw materials, which are defined by the grade mark, grade stamp, mill certificate, Listings, certified reports, duly authenticated reports from approved agencies, and research reports prepared by approved agencies and/or approved sources provided by the suppliers of products, materials, designs, assemblies and/or methods of construction. These are presumed to be minimum properties and relied upon to be accurate. The reliability of DrJ's engineering practice, as contained in this report, may be dependent upon published design properties by others.
- 7.5 Testing and Engineering Analysis:
 - 7.5.1 The strength, rigidity and/or general performance of component parts and/or the integrated structure are determined by suitable tests that simulate the actual conditions of application that occur and/or by accepted engineering practice and experience.
- 7.6 Where additional condition of use and/or code compliance information is required, please search for ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing on the DrJ Certification website.





8 Findings

- As delineated in **Section 3**, ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing have performance characteristics that were tested and/or meet pertinent standards and is suitable for use pursuant to its specified purpose.
- 8.2 When used and installed in accordance with this report and the manufacturer installation instructions,
 ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing shall be approved for
 the following applications:
 - 8.2.1 Lateral (in-plane) load resistance due to wind and seismic loads carried by shear walls.
 - 8.2.2 Transverse (perpendicular-to-plane) load resistance due to components and cladding pressures on building surfaces.
 - 8.2.3 Resistance to uplift loads in single top plate applications.
 - 8.2.4 Performance for use as a WRB in accordance with NBC Division B Note A-5.6.2.1.
 - 8.2.5 Performance for use as an air barrier in accordance with NBC Division B Section 5.4 and Subsection 9.25.3.
 - 8.2.6 Surface Burn Characteristics in accordance with **Table 5**.
- 8.3 Any application specific issues not addressed herein can be engineered by an RDP. Assistance with engineering is available from Amrize Building Envelope, LLC.
- 8.4 These innovative products have been evaluated in the context of the codes listed in **Section 2** and are compliant with all known provincial, territorial, and local building codes. Where there are known variations in provincial, territorial, or local codes applicable to this report, they are listed here.
 - 8.4.1 No known variations
- 8.5 NBC Volume 1 Relationship of the NBC to Standards Development and Conformity Assessment:

Certification

Certification is the confirmation by an independent organization that a product, service, or system meets a requirement...Certification bodies publish lists of certified products and companies...Several organizations, including the Canadian Construction Materials Centre (CCMC), offer such evaluation services.

Evaluation

An evaluation is a written opinion by an independent professional organization that a product will perform its intended function. An evaluation is very often done to determine the ability of an innovative product, for which no standards exist, to satisfy the intent of the Code requirement...

- 8.6 <u>ISO/IEC 17065 accredited third-party certification bodies</u>, including but not limited to, <u>Standards Council of Canada</u> (SCC) and <u>ANSI National Accreditation Board</u> (ANAB), confirm that product certification bodies have the expertise to provide technical evaluation services within their scope of accreditation. All SCC and ANAB product certification bodies meet NBC requirements to offer evaluation services for alternative solutions.
 - 8.6.1 DrJ is an ISO/IEC 17065 <u>ANAB-Accredited Product Certification Body</u> <u>Accreditation #1131</u> and employs professional engineers. 10
- 8.7 Through ANAB accreditation and the <u>IAF Multilateral Agreements</u>, this report can be used to obtain product approval in any <u>jurisdiction</u> or country that has <u>IAF MLA Members & Signatories</u> to meet the <u>Purpose of the MLA</u> "certified once, accepted everywhere." IAF specifically says, "Once an accreditation body is a signatory of the IAF MLA, it is required to recognise certificates and validation and verification statements issued by conformity assessment bodies accredited by all other signatories of the IAF MLA, with the appropriate scope."¹¹





- 8.8 Product certification organizations, accredited by the SCC and ANAB, are defined as equivalent evaluation services:
 - 8.8.1 Canada-United States-Mexico Agreement (CUSMA), Article 11.6 Conformity Assessment confirms mutual recognition by stating, "...each Party shall accord to conformity assessment bodies located in the territory of another Party treatment no less favorable than that it accords to conformity assessment bodies located in its own territory or in the territory of the other Party."
 - 8.8.2 The SCC National Conformity Assessment Principles states, "SCC is a member of a number of international organizations developing voluntary conformity assessment agreements that help ensure the international acceptance of Canadian conformity assessment results. Signatories to these agreements (like SCC) recognize each other's accreditations as being equivalent to their own." 12
- 8.9 Building official approval of a licensed professional engineer is performed by verifying the professional engineer and/or their business entity are listed by the engineering regulators of the relevant jurisdiction.

9 Conditions of Use

- 9.1 Material properties shall not fall outside the boundaries defined in **Section 3**.
- 9.2 As defined in **Section 3**, where material and/or engineering mechanics properties are created for load resisting design purposes, the resistance to the applied load shall not exceed the ability of the defined properties to resist those loads using the principles of accepted engineering practice.
- 9.3 As listed herein, ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing shall not be used:
 - 9.3.1 As a nailing base for claddings, trim, windows, and doors. Fastening through the ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing into the framing is acceptable.
 - 9.3.2 To resist horizontal loads from concrete and masonry walls.
- 9.4 When ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing are installed as a wall sheathing but are not installed per structural requirements, light-framed walls shall be braced by other means. When used as a WRB, installation shall be in accordance with **Section 5.3**.
 - 9.4.1 When ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing are not installed as a WRB, other means of providing a WRB may be required, as per the relevant code.
- 9.5 When used in high wind and high seismic areas as defined in NBC Division B Sentence 9.23.13.2.(1), bracing to resist lateral loads shall be designed and constructed in accordance with NBC Division B Part 4 or good engineering practice in accordance with NBC Division B Sentence 9.23.13.2.(2).
- 9.6 When used in extreme wind and extreme seismic areas as defined in NBC Division B Sentence 9.23.13.3.(1), bracing to resist lateral loads shall be designed and constructed in accordance with NBC Division B Sentence 9.23.13.3.(2). Design loads shall be determined in accordance with the building code adopted by the jurisdiction in which the project is to be constructed.
 - 9.6.1 Specified shear strengths shall not exceed values in **Table 1** for wind loads and **Table 2** for seismic loads.
 - 9.6.2 Factored uplift loads shall not exceed values in **Table 3**.
 - 9.6.3 Transverse design loads shall not exceed those described in **Table 4**, unless an approved exterior wall covering capable of separately resisting loads perpendicular to the face of the walls is installed over the sheathing.
- 9.7 ThermoPLY Red Structural Sheathing and ThermoPLY Red AMG Structural Sheathing are manufactured under a quality control program with quality control inspections established by the governing legislation of the adopting province or territory, as described in the NBC Volume 1 commentary on Conformity Assessment.





- 9.8 Where required by regulation and enforced by the building official, also known as the authority having jurisdiction (AHJ) in which the project is to be constructed:
 - 9.8.1 Any calculations incorporated into the construction documents shall conform to accepted engineering practice, and, when prepared by an <u>approved source</u>, shall be approved when signed and sealed.
 - 9.8.2 This report and the installation instructions shall be submitted at the time of permit application.
 - 9.8.3 These innovative products have an internal quality control program and a third-party quality assurance program.
 - 9.8.4 At a minimum, these innovative products shall be installed per **Section 6** of this report.
 - 9.8.5 This report shall be reviewed for code compliance by the AHJ in concert with the duties and powers granted to the building official by the provincial regulations governing such duties and powers.
 - 9.8.6 The application of these innovative products in the context of this report are dependent on the accuracy of the construction documents, implementation of installation instructions, inspections, and any other regulatory requirements that may apply.
- 9.9 Design loads shall be determined in accordance with the building code adopted by the jurisdiction in which the project is to be constructed and/or by the designer (e.g., owner).
- 9.10 The actual design, suitability, and use of this report, for any particular building, is the responsibility of the owner or the authorized agent of the owner.

10 Identification

- 10.1 The innovative products listed in **Section 1.1** are identified by a label on the board or packaging material bearing the manufacturer name, product name, report number, and other information to confirm code compliance.
- 10.2 Additional technical information can be found at www.oxengineeredproducts.com.

11 Review Schedule

- 11.1 This report is subject to periodic review and revision. For the most recent version, visit dricertification.org.
- 11.2 For information on the status of this report, contact DrJ Certification.





Notes

- 1 For more information, visit <u>dricertification.org</u> or call us at 608-310-6748.
- 2 Unless otherwise noted, all references in this report are from the 2020 version of the NBC. This alternative solution is also approved for use with the 2010 and 2015 NBC and the standards referenced therein.
- 3 18 U.S. Code § 1831 Economic espionage Whoever, intending or knowing that the offense will benefit any foreign government, foreign instrumentality, or foreign agent, knowingly steals, or without authorization appropriates, takes, carries away, or conceals, or by fraud, artifice, or deception obtains a trade secret shall be fined not more than \$5,000,000 or imprisoned not more than 15 years, or both. Any organization that commits any offense described shall be fined not more than the greater of \$10,000,000 or 3 times the value of the stolen trade secret to the organization, including expenses for research and design and other costs of reproducing the trade secret that the organization has thereby avoided. https://www.law.cornell.edu/uscode/text/18/part-l/chapter-90.
- 4 ANAB is part of the <u>USMCA</u> and <u>IAF MLA</u>, where the purpose of these agreements are to ensure mutual recognition of accredited certification and validation/verification statements between agreement signatories, and subsequent acceptance of ANAB accredited certification and validation/verification statements by professional engineers based upon having one universal approval process for the timely approval of innovative materials, products, designs, services, assemblies and/or methods of construction.
- ⁵ https://anabpd.ansi.org/Accreditation/product-certification/DirectoryListingAccredited?menuID=1&prgID=1
- 6 https://iaf.nu/en/member-details/?member_id=91
- https://iaf.nu/en/member-details/?member_id=14
- 8 NBC Division A Clause A-1.2.1.1.(1)(b) provides information on code compliance via alternative solutions and defines alternative solutions as "...achiev[ing] at least the minimum level of performance required by Division B." NBC Division C Section 2.3 includes additional guidance for documentation of alternative solutions.
- 9 https://anabpd.ansi.org/Accreditation/product-certification/AllDirectoryDetails?&prgID=1&OrgId=2125&statusID=4
- 10 Through ANAB accreditation and the <u>IAF MLA</u>, DrJ certification can be used to obtain material, product, design, or method of construction approval in any jurisdiction or country that has <u>IAF MLA Members & Signatories</u> to meet the <u>Purpose of the MLA</u> "certified once, accepted everywhere".
- 11 https://iaf.nu/en/about-iaf-mla/#:~:text=required%20to%20recognise
- The National Conformity Assessment Principles states, "Product regulations and standards may vary from country to country. If these are set arbitrarily, they could be deemed as protectionist. The World Trade Organization (WTO) Agreement on Technical Barriers to Trade (TBT Agreement) is intended to ensure that technical regulations, standards and conformity assessment procedures of member countries do not create unnecessary obstacles to trade. Under the TBT Agreement, members of the WTO agree to use international standards, including conformity assessment standards and guides, as a basis for their technical requirements."