



Listing and Technical Evaluation Report™

A Duly Authenticated Report from an Approved Agency

Report No: 2304-117



Issue Date: November 29, 2023 Revision Date: June 20, 2025

Subject to Renewal: July 1, 2026

Performance Characteristics of Millboard® Composite Siding

Trade Secret Report Holder:

Millboard[®] Company, Ltd.

Phone: 651-207-4175

Website: www.millboard.com

Email: inquiries@millboard.com

CSI Designations:

DIVISION: 07 00 00 - THERMAL AND MOISTURE PROTECTION Section: 07 46 33 - Plastic Siding

1 Innovative Products Evaluated¹

- 1.1 Millboard Composite Siding:
 - 1.1.1 Shadow Line+
 - 1.1.2 Board & Batten+

2 Product Description and Materials

2.1 The innovative products evaluated in this report are shown in **Figure 1**, **Figure 2**, and are described in **Table 1**.





Figure 2. Board & Batten+ Siding





Table 1.	Millboard	Composite	Sidina	Specifications
	i i i i i i i i i i i i i i i i i i i	Composito	Claing	opoonnoutionio

Deremeter	Product					
Farameter	Shadow Line+	Board & Batten+				
Standard Length	141 ³ /4" (3,600 mm)					
Nominal Width	Width: 7 ⁷ / ₈ " (200 mm) Installed Width: 7 ¹ / ₈ " (181 mm)	Width: 7 ⁷ /8" (200 mm) Installed Width: 7 ¹ /8" (181 mm)				
Nominal Thickness	^{11/} 16" (18 mm)	1" (⁹ / ₁₆ " Board + ⁷ / ₁₆ " Batten); 26 mm (14 mm Board + 12 mm Batten)				
Available Colors ¹	Anthracite, Antique Oak, Burnt Cedar, Coppered Oak, Golden Oak, Limed Oak, Sage Green, Salt Blue, Smoked Oak	Anthracite, Antique Oak, Burnt Cedar, Coppered Oak, Golden Oak, Limed Oak, Jarrah, Smoked Oak				
1 See Figure 3 and Figure 4 for additional datails						

Available colors:



.

MCL360R











Limed Oak: MCL360L

......

Anthracite: MCL360X MCL360A Coppered Oak: Golden Oak: MCL360G

Sage Green: MCL360N MCL360T Smoked Oak: MCL360D

Figure 3. Available Colors for Shadow Line+ Profile

MCL360C

Available colors:							
Limed Oak Burnt Co	edar Anthracite	Antique Oak	Coppered Oak	Golden Oak	Smoked Oak	Jarrah	
MCBF360L MCBF36	OR MCBF360X	MCBF360A	MCBF360C	MCBF360G	MCBF360D	MCBF360	

Figure 4. Available Colors for Board & Batten+ Profile

- 2.2 Millboard Composite Sidings are wood-free siding products comprised of a proprietary fire-retardant rubberized coating, melded to a fiberglass reinforced resin-mineral composite core with a UV stabilized 2K coating.
- 2.3 As needed, review material properties for design in Section 6 and the regulatory evaluation in Section 8.





3 Definitions²

- 3.1 <u>New Materials³</u> are defined as building materials, equipment, appliances, systems, or methods of construction, not provided for by prescriptive and/or legislatively adopted regulations, known as alternative materials.⁴ The <u>design strength</u> and permissible stresses shall be established by tests⁵ and/or engineering analysis.⁶
- 3.2 <u>Duly authenticated reports</u>⁷ and <u>research reports</u>⁸ are test reports and related engineering evaluations that are written by an <u>approved agency</u>⁹ and/or an <u>approved source</u>.¹⁰
 - 3.2.1 These reports utilize intellectual property and/or trade secrets to create public domain material properties for commercial end-use.
 - 3.2.1.1 This report protects confidential Intellectual Property and trade secretes under the regulation, <u>18.US.Code.90</u>, also known as <u>Defend Trade Secrets Act of 2016</u> (DTSA).¹¹
- 3.3 An approved agency is *"approved"* when it is <u>ANAB ISO/IEC 17065 accredited</u>. DrJ Engineering, LLC (DrJ) is accredited and listed in the <u>ANAB directory</u>.
- 3.4 An <u>approved source</u> is *"approved"* when a professional engineer (i.e., <u>Registered Design Professional</u>, hereinafter <u>RDP</u>) is properly licensed to transact engineering commerce. The regulatory authority governing approved sources is the <u>state legislature</u> via its professional engineering regulations.¹²
- 3.5 Testing and/or inspections conducted for this <u>duly authenticated report</u> were performed by an <u>ISO/IEC 17025</u> <u>accredited testing laboratory</u>, an <u>ISO/IEC 17020 accredited inspection body</u>, and/or a licensed <u>RDP</u>.
 - 3.5.1 The <u>Center for Building Innovation</u> (CBI) is <u>ANAB¹³ ISO/IEC 17025</u> and <u>ISO/IEC 17020</u> accredited.
- 3.6 The regulatory authority shall <u>enforce</u>¹⁴ the specific provisions of each legislatively adopted regulation. If there is a non-conformance, the specific regulatory section and language of the non-conformance shall be provided in <u>writing</u>¹⁵ stating the nonconformance and the path to its cure.
- 3.7 The regulatory authority shall accept <u>duly authenticated reports</u> from an <u>approved agency</u> and/or an <u>approved</u> <u>source</u> with respect to the quality and manner of use of new materials or assemblies as provided for in regulations regarding the use of alternative materials, designs, or methods of construction.¹⁶
- 3.8 ANAB is an <u>International Accreditation Forum</u> (IAF) <u>Multilateral Recognition Arrangement</u> (MLA) signatory. Therefore, recognition of certificates and validation statements issued by conformity assessment bodies accredited by all other signatories of the IAF MLA with the appropriate scope shall be approved.¹⁷ Thus, all ANAB ISO/IEC 17065 <u>duly authenticated reports</u> are approval equivalent,¹⁸ and can be used in any country that is an MLA signatory found at this link: <u>https://iaf.nu/en/recognised-abs/</u>
- 3.9 Approval equity is a fundamental commercial and legal principle.¹⁹

4 Applicable Local, State, and Federal Approvals; Standards; Regulations²⁰

- 4.1 Local, State, and Federal
 - 4.1.1 Approved in all local jurisdictions pursuant to ISO/IEC 17065 <u>duly authenticated report</u> use, which includes the following featured local jurisdictions and is not limited to: Austin, Baltimore, Broward County, Chicago, Clark County, Dade County, Dallas, Detroit, Denver, DuPage County, Fort Worth, Houston, Kansas City, King County, Knoxville, Las Vegas, Los Angeles City, Los Angeles County, Miami, Nashville, New York City, Omaha, Philadelphia, Phoenix, Portland, San Antonio, San Diego, San Jose, San Francisco, Seattle, Sioux Falls, South Holland, Texas Department of Insurance, and Wichita.²¹
 - 4.1.2 Approved in all state jurisdictions pursuant to ISO/IEC 17065 <u>duly authenticated report</u> use, which includes the following featured states, and is not limited to: California, Florida, New Jersey, Oregon, New York, Texas, Washington, and Wisconsin.²²





- 4.1.3 Approved by the Code of Federal Regulations Manufactured Home Construction: Pursuant to Title 24, Subtitle B, Chapter XX, Part 3282.14²³ and Part 3280²⁴ pursuant to the use of ISO/IEC 17065 <u>duly</u> <u>authenticated reports</u>.
- 4.1.4 Approved means complying with the requirements of local, state, or federal legislation.

4.2 Standards

- 4.2.1 ASCE 7: Minimum Design Loads and Associated Criteria for Buildings and Other Structures
- 4.2.2 ASTM D1761: Standard Test Methods for Mechanical Fasteners in Wood and Wood-Based Materials
- 4.2.3 ASTM E84: Standard Test Method for Surface Burning Characteristics of Building Materials
- 4.2.4 BS EN 317: Particleboards and Fibreboards Determination of Swelling in Thickness after Immersion in Water
- 4.2.5 BS EN 322 Wood-Based Panels Determination of Moisture Content
- 4.2.6 BS EN 438-2: High-Pressure Decorative Laminates (HPL) Sheets Based on Thermosetting Resins (Usually call Laminates) Part 2: Determination of Properties, Section 26 Resistance to Staining
- 4.2.7 BS EN 13245-1: Plastics Unplasticized Poly(Vinyl Chloride) (PVC-U) Profiles for Building Applications Part 1: Designation of PVC-U Profiles, Annex B Determination of the Impact Resistance
- 4.2.8 EN ISO 7784-2: Paints and Varnishes Determination of Resistance to Abrasion Part 2: Method with Abrasive Rubber Wheels and Rotating Test Specimen
- 4.2.9 MOAT 27: General Directive for the Assessment of Roof Waterproofing Systems
- 4.2.10 MOAT 43: UEAtc Directives for Impact Testing Opaque Vertical Building Components
- 4.2.11 SFM 12-7A-1: Materials and Construction Methods for Exterior Wildfire Exposure
- 4.2.12 Technical Bulletin LL-9025: Outdoor Weathering: Basic Exposure Procedures

4.3 Regulations

- 4.3.1 IBC 15, 18, 21, 24: International Building Code®
- 4.3.2 IRC 15, 18, 21, 24: International Residential Code®
- 4.3.3 IECC 15, 18, 21, 24: International Energy Conservation Code®
- 4.3.4 FBC-B—20, 23: Florida Building Code Building²⁵ (FL 47417)
- 4.3.5 FBC-R—20, 23: Florida Building Code Residential²⁵ (FL 47417)
- 4.4 Installation of Millboard Composite Siding over foam plastic sheathing is outside the scope of this report.
- 4.5 Use of Millboard Composite Siding in fire-resistance rated assemblies is outside the scope of this report.

5 Listed²⁶

5.1 Equipment, materials, products, or services included in a List published by a <u>nationally recognized testing</u> <u>laboratory</u> (i.e., CBI), an <u>approved agency</u> (i.e., CBI and DrJ), and/or and <u>approved source</u> (i.e., DrJ), or other organization(s) concerned with product evaluation (i.e., DrJ), that maintains periodic inspection (i.e., CBI) of production of listed equipment or materials, and whose listing states either that the equipment or material meets nationally recognized standards or has been tested and found suitable for use in a specified manner.





6 Tabulated Properties Generated from Nationally Recognized Standards

6.1 Millboard Composite Sidings are used as exterior wall coverings in accordance with the applicable sections of IBC Chapter 14 and IRC Section R703, and are installed over walls capable of supporting the imposed loads in accordance with IBC Section 1609 and IRC Section R301.2.1.

6.2 Transverse Wind Load

6.2.1 The allowable wind load resistance capacity is presented in **Table 2** and **Table 3**.

 Table 2. Allowable Positive and Negative Wind Loads per Fastening Configuration – Shadow Line+

Product	Substrate	Fastener	Vertical Fastener Spacing, spv ¹ (in o.c.)	Horizontal Fastener Spacing, sph ² (in o.c.)	Allowable Capacity ³ (Ib/fastener)	Allowable Wind Pressure (psf)
		#8 x 2" Flat Head	71/2	16	65	80
	7/ # 0.05	Wood Screw	1 18	24	00	55
	7/16" OSB	0.092" x 2"	74/	16		30
		Galvanized Ring Shank Nail	7 1/8	24	25	20
Shadow Line+	2 x 4 SPF	#8 x 2" Flat Head	71/2	16	100	125
		Wood Screw	1718	24	100	85
·	Sawn Lumber	0.092" x 2"	-44	16	10	50
		Galvanized Ring Shank Nail	71/8	24	40	35
	20 gauge CES	#8 x 11/2" Flat Head	71/2	16	70	90
	20-yauge CFS	Sheet Metal Screw	1 18	24	70	60

SI: 1 in = 25.4 mm, 1 lb = 4.448 N, 1 psf = 47.88 Pa

1. One fastener installed through the tongue of the product into the substrate.

2. Horizontal spacing is based on typical stud spacing.

3. Allowable capacity is based on the lower of withdrawal strength or head pull-through strength of the fasteners used for installation.





Table 3. Allowable Positive and Negative Wind Loads per Fastening Configuration – Board & Batten+

Product	Substrate	Fastener	Vertical Fastener Spacing, spv ¹ (in o.c.)	Horizontal Fastener Spacing, spʰ² (in o.c.)	Allowable Capacity ³ (Ib/fastener)	Allowable Wind Pressure (psf)
		#8 x 2" Flat Head	71/2	16	65	80
	7/ # 0.05	Wood Screw	1 18	24	00	55
	7/16" OSB	0.092" x 2"		16		30
		Shank Nail	7 1/8	24	20	20
Poord & Patton	2 x 4 SPF	#8 x 2" Flat Head	71/2	16	70	90
DUAIU & DAILEIIT		Wood Screw	1 18	24	70	60
	Sawn Lumber	0.092" x 2"	747	16	05	50
-		Galvanized Ring Shank Nail	7 ¹ /8	24	25	35
		#8 x 11/2" Flat Head	71/2	16	65	95
	20-yauye OI O	Sheet Metal Screw	1 18	24	00	65

SI: 1 in = 25.4 mm, 1 lb = 4.448 N, 1 psf = 47.88 Pa

1. One fastener installed through the tongue of the product into the substrate at each stud location.

2. Horizontal spacing is based on typical stud spacing.

3. Allowable capacity is based on the lower of withdrawal strength or head-pull-through strength of the fasteners used for installation.





6.3 Wind Speed

6.3.1 Basic and allowable wind speeds are shown in **Table 4** and **Table 5**.

Product	Substrate	Fastener	Vertical Fastener	Horizontal Fastener	Maximum Wind Speed, V _{ult} (mph)			Allowable Wind Speed, V _{asd} (mph)		
Troudot	oussilute	T dottener	Spacing, (in o.c.)	Spacing, (in o.c.)	В	С	D	В	С	D
		#8 x 2" Flat	71/2	16	200	200	185	155	155	145
		Screw	1 18	24	195	165	150	150	130	115
7/ ₁₆ " OSB	0.092" x 2" Galvanized	71/	16	145	120	110	110	95	85	
		Ring Shank Nail	7.78	24	120	100	90	95	75	70
		#8 x 2" Flat	Flat /ood 7¹/ ₈ w	16	200	200	200	155	155	155
Line+		Screw		24	200	200	190	155	155	145
Sa	Sawn Lumber	0.092" x 2" Galvanized	71/0	16	185	155	145	145	120	110
		Ring Shank Nail	178	24	155	130	120	120	100	95
20-gauge CFS	20-gauge	#8 x 11/2" Flat	71/-	16	200	200	195	155	155	150
	Metal Screw	1 18	24	200	170	160	155	130	125	

Table 4. Maximum Basic Wind Speeds – Shadow Line+1

SI: 1 in = 25.4 mm, 1 lbf = 4.448 N, 1 psf = 47.88 Pa, 1 mph = 0.447 m/s

1. Based on:

a. A building height of 30-feet, GC_p= -1.4 for Zone 5 and an Effective Wind Area of 10 ft², Topographic Factor: K_{zt}=1.0, Ground Elevation Factor: K_e=1.0, Internal Pressure Coefficient, GC_p=+/-0.18 for an enclosed building, K_d = 0.85 for 'Component and Siding'

b. V_{ult} is limited to 200 mph.

 $V_{asd} = V_{ult}\sqrt{0.6}$. V_{asd} is limited to 155 mph (200 $\sqrt{0.6}$).





Product Substrate		Vertical Fastener	Vertical Fastener	tical Horizontal tener Fastener		Maximum Wind Speed, V _{ult} (mph)			Allowable Wind Speed, V _{asd} (mph)		
Troudot	oussilute		Spacing, (in o.c.)	Spacing, (in o.c.)	В	С	D	В	С	D	
		#8 x 2" Flat	71/2	16	200	200	185	155	155	145	
		Screw	1.18	24	195	165	150	150	130	115	
	7/ ₁₆ " OSB	0.092" x 2" Galvanized	7 ¹ /8	16	145	120	110	110	95	85	
Board &		Ring Shank Nail		24	120	100	90	95	75	70	
	#8 x 2" Flat	3 x 2" Flat	16	200	200	195	155	155	150		
Batten+	Batten+	Screw	1.18	24	200	170	160	155	130	125	
Sawn Lumbe	Sawn Lumber	0.092" x 2" Galvanized	0.092" x 2" Galvanized Ring Shank Nail	16	185	155	145	145	120	110	
		Ring Shank Nail		24	155	130	120	120	100	95	
	20-gauge	#8 x 11/2" Flat	71/2	16	200	200	200	155	155	155	
CFS	Metal Screw	24	200	180	165	155	140	130			

Table 5. Maximum Basic Wind Speeds – Board & Batten+1

SI: 1 in = 25.4 mm, 1 lbf = 4.448 N, 1 psf = 47.88 Pa, 1 mph = 0.447 m/s

1. Based on:

c. A building height of 30-feet, GC_p= -1.4 for Zone 5 and an Effective Wind Area of 10 ft², Topographic Factor: K_{zt}=1.0, Ground Elevation Factor: K_e=1.0, Internal Pressure Coefficient, GC_p=+/-0.18 for an enclosed building, K_d = 0.85 for 'Component and Siding'

d. V_{ult} is limited to 200 mph.

 $V_{asd} = V_{ult}\sqrt{0.6}$. V_{asd} is limited to 155 mph (200 $\sqrt{0.6}$).

6.4 Surface Burning Characteristics

6.4.1 Flame spread testing was conducted in accordance with ASTM E84 and test results are shown in **Table 6**.

Table 6.	Surface	Burning	Characteristics
----------	---------	---------	-----------------

Product	Flame Spread Index	Flame Spread Classification
Shadow Line+	< 25	Class A
Board & Batten+	< 25	Class A





6.5 Exterior Wildfire Exposure

6.5.1 Exterior wildfire exposure testing was completed in accordance with SFM 12-7A-1 for various assemblies as found in **Table 7**.

Assembly Designation	Exterior Wall Covering Assembly Components (Listed Exterior to Interior)	Test Result
	Shadow Line+ Siding	
	Hydrowrap Hydrogap Drainable Housewrap	
	⁵ /8" Type X Gypsum Wallboard	Pass
	7/ ₁₆ " Oriented Strand Board (OSB)	
	2 x 4 Studs	
	Shadow Line+ Siding	
	Slicker Classic Rainscreen	
	Flatwrap Housewrap	Dass
	⁵ / ₈ " Type X Gypsum Wallboard	1 455
	7/ ₁₆ " OSB	
Millboard Composite Siding	2 x 4 Studs	
	Shadow Line+ Siding	
	Flatwrap Housewrap	
	⁵ /8" Type X Gypsum Wallboard	Pass
	7/ ₁₆ " OSB	
	2 x 4 Studs	
	Board & Batten+	
	Hydrowrap Hydrogap Drainable Housewrap	
	5/8" Type X Gypsum Wallboard	Pass
	7/ ₁₆ " OSB	
	2 x 4 Studs	

Table 7. Assembly Testing for Exposure to Exterior Wildfires





6.6 Hard Body Impact

- 6.6.1 Hard body impact was conducted in accordance with MOAT 43 on Millboard Composite Siding.
- 6.6.2 At an impact energy of 10 N⋅m (Joule) using 1 kg steel ball with a diameter of 63.5 mm, no visible damage was observed.

6.7 Impact Resistance

- 6.7.1 Impact testing was conducted in accordance with BS EN 13245-1 using a 4.4 lb (2 kg), smooth hemispherical surface of 1" (25 mm) radius and a fall height of 39³/₈" (1,000 mm) at a support span of 4" (100 mm) on aged Millboard Composite Siding products.
 - 6.7.1.1 Accelerated weathering consisted of 140° F (60° C) and UV-A exposure for five (5) hours followed by one-hour spray cycles for a total of 5,000 hours.
 - 6.7.1.2 No cracking or damage to the topcoat with any impact.
 - 6.7.1.3 Slight indentation to the surface (visible with aid of surface illumination, but difficult to see under normal lighting conditions).

6.8 Static Indentation

- 6.8.1 Static indentation was conducted in accordance with MOAT 27 on Millboard Composite Siding products.
- 6.8.2 Millboard Composite Sidings were subjected to a 10 kg load via a 10 mm diameter surface for 41 days. The results are shown in **Table 8**.

Table 8. Static Indentation

Product	Indentation, in (mm)
Millboard Composite Siding	0.004 (0.1)

6.9 Abrasion Resistance

6.9.1 Millboard Composite Siding products were evaluated to assess abrasion resistance in accordance with EN ISO 7784-2 utilizing the Taber Abrader test machine fitted with CS-17 wheels, with an applied load of 1 kg and a total duration of 1,000 cycles. The results are shown in **Table 9**.

Table 9. Abrasion Resistance

Product	Average Weight Loss After 500 Cycles (mg)	Average Weight Loss After 1,000 Cycles (mg)				
Millboard Composite Siding	152	261				
. Tested in accordance with BS EN 322 (equivalent to ASTM 4442). Tested in accordance with BS EN 317 with an immersion time of 24 hours.						

6.10 Protection Against Decay

6.10.1 Millboard Composite Sidings contain no wood or cellulosic materials and meet the requirements of <u>IBC</u> <u>Section 2304.12</u> and <u>IRC Section R304</u>²⁷ where protection against biodegradation and decay is required.

6.11 *Protection Against Termites*

6.11.1 Millboard Composite Sidings contain no wood or cellulosic materials and meet the requirements of <u>IBC</u> Section 2304.12 and <u>IRC Section R305</u>²⁸ where protection against termite attack is required.





6.12 Moisture Content and Thickness Swell

6.12.1 Millboard Composite Sidings were evaluated to assess swelling and moisture content after immersion in water in accordance with BS EN 317, and BS EN 322. The results are shown in **Table 10**.

Table 10. Moisture Content and Thickness Swell¹

Product	Average Moisture Content ¹ (%)	Average Swelling ² (%)			
Millboard Composite Siding	0.6	0.10			
 Tested in accordance with BS EN 322 (equivalent to ASTM 4442). Tested in accordance with BS EN 317 with an immersion time of 24 hours. 					

6.13 Fade Resistance

- 6.13.1 Millboard Composite Sidings were evaluated to assess fade resistance by subjecting the product to outdoor exposure for 24 months.
 - 6.13.1.1 Testing was conducted in accordance with <u>Q-Lab Technical Bulletin, LL-9025</u>.
 - 6.13.1.2 Test location was Florida with an exposure angle of 5° south.
 - 6.13.1.3 The results are presented in **Table 11**.
 - 6.13.1.4 Lightness Factor (L):
 - 6.13.1.4.1 The measured object's lightness or darkness is quantified by the "*L*" number on a scale of zero to 100, where 0=black, 50=grey, and 100=white.

6.13.1.5 Red/Green Factor (a):

- 6.13.1.5.1 The object's redness or greenness is quantified by the "a" number. When the "a" value is a positive number, the measured object is a red color. The higher the number, the more red the object is. When an "a" is a negative number, the measured object is a green color. The lower the number, the greener the color. A value of zero for "a" would be exactly intermediate between red and green.
- 6.13.1.6 Blue/Yellow Factor (b):
 - 6.13.1.6.1 The object's yellowness or blueness is quantified by the "b" number. When the "b" is a positive number, the object is yellow. The larger the number, the more yellow the object. When the "b" value is a negative number, a blue colored object is indicated. The lower the number, the more intense the color. A value of zero would be intermediate between yellow and blue.





Millboard Composite Siding Product Colors	Original			Final			Difference		
	L	а	b	Ľ	a'	b'	L	а	b
Limed Oak	67.5	3.0	11.5	68.7	2.8	10.8	1.1	-0.2	-0.7
Smoked Oak	57.0	0.0	6.0	58.5	0.2	6.8	1.6	0.3	0.8
Golden Oak	54.7	7.0	18.8	54.8	6.6	18.4	0.1	-0.4	-0.3
Coppered Oak	38.7	8.5	17.7	43.6	7.5	18.4	5.0	-0.9	0.8
Antique Oak	34.1	5.8	12.7	37.5	4.4	10.4	3.4	-1.5	-2.3
Jarrah	32.3	17.4	18.0	38.0	14.2	17.1	5.7	-3.2	-0.9
Burnt Cedar	23.6	0.3	-0.8	29.7	-0.1	0.4	6.2	-0.4	1.1

Table 11. Fade Resistance

6.14 Resistance to Staining

6.14.1 Millboard Composite Sidings were evaluated to assess resistance to staining and results are shown in **Table 12**.

T	able	12.	Stain	Resistance

Product	Cover	Cover Staining Agent Rating ¹		Observations ²	
Millboard Composite Siding Products	Acetone	5	No visible change	Acetone	
	Coffee	4	Slight change of color (visible at certain angles)	Coffee	
	Sodium Hydroxide	5	No visible change	Sodium Hydroxide	
	Hydrogen Peroxide	5	No visible change	Hydrogen Peroxide	
	Shoe Polish	5	No visible change	Shoe Polish	
	Acetone	5	No visible change	Acetone	
	Coffee	4	Slight change of color (visible at certain angles)	Coffee	
	Sodium Hydroxide	5	No visible change	Sodium Hydroxide	
	Hydrogen Peroxide	5	No visible change	Hydrogen Peroxide	
	Shoe Polish	5	No visible change	Shoe Polish	

1. Placed over staining agent to restrict evaporation during the allotted exposure time.

2. In accordance with Section 15.6 of BS EN 438-2.

6.15 Where the application falls outside of the performance evaluation, conditions of use, and/or installation requirements set forth herein, alternative techniques shall be permitted in accordance with accepted engineering practice and experience. This includes but is not limited to the following areas of engineering: mechanics or materials, structural, building science, and fire science.





7 Certified Performance²⁹

- 7.1 All construction methods shall conform to accepted engineering practices to ensure durable, livable, and safe construction and shall demonstrate acceptable workmanship reflecting journeyman quality of work of the various trades.³⁰
- 7.2 The strength and rigidity of the component parts and/or the integrated structure shall be determined by engineering analysis or by suitable load tests to simulate the actual loads and conditions of application that occur.³¹

8 Regulatory Evaluation and Accepted Engineering Practice

- 8.1 Millboard Composite Sidings (Shadow Line+ and Board & Batten+) comply with the following legislatively adopted regulations and/or accepted engineering practice for the following reasons:
 - 8.1.1 For use as an exterior wall covering on new or existing concrete or masonry walls in accordance with <u>IBC</u> <u>Section 1402³²</u> and <u>IRC Section R703</u>.
 - 8.1.2 For use as a weather-resistant covering in accordance with <u>IBC Section 1403.2</u>³³ and <u>IRC Section</u> <u>R703.1.1</u>.
 - 8.1.3 To determine the ability of Millboard Composite Sidings to resist wind loads in accordance with <u>IBC</u> Section 1609 and <u>IRC Section R703.1.2</u>.
- 8.2 Any building code, regulation and/or accepted engineering evaluations (i.e., <u>research reports</u>, <u>duly</u> <u>authenticated reports</u>, etc.) that are conducted for this Listing were performed by DrJ, which is an <u>ISO/IEC</u> <u>17065 accredited certification body</u> and a professional engineering company operated by <u>RDP</u> or <u>approved</u> <u>sources</u>. DrJ is qualified³⁴ to practice product and regulatory compliance services within its <u>scope of</u> <u>accreditation and engineering expertise</u>,³⁵ respectively.
- 8.3 Engineering evaluations are conducted with DrJ's ANAB <u>accredited ICS code scope</u> of expertise, which is also its areas of professional engineering competence.
- 8.4 Any regulation specific issues not addressed in this section are outside the scope of this report.

9 Installation

- 9.1 Installation shall comply with the approved construction documents, the manufacturer installation instructions, this report, and the applicable building code.
- 9.2 In the event of a conflict between the manufacturer installation instructions and this report, contact the manufacturer for counsel on the proper installation method.
- 9.3 Millboard Composite Siding products can be installed horizontally or vertically. **Table 2** through **Table 5** are applicable to either orientation.





10 Substantiating Data

- 10.1 Testing has been performed under the supervision of a professional engineer and/or under the requirements of ISO/IEC 17025 as follows:
 - 10.1.1 Fastener withdrawal, head-pull-through, and lateral resistance in accordance with ASTM D1761
 - 10.1.2 Wind pressure calculations in accordance with general engineering principles by DrJ Engineering, LLC
 - 10.1.3 Wind speed calculations in accordance with Chapter 30 of ASCE 7 by DrJ Engineering, LLC
 - 10.1.4 Surface burning characteristics in accordance with ASTM E84
 - 10.1.5 Fire testing in accordance with SFM 12-7A-1
 - 10.1.6 Impact testing in accordance with MOAT 43, BS EN 13245-1, and MOAT 27
 - 10.1.7 Abrasion resistance in accordance with EN ISO 7784-2
 - 10.1.8 Moisture content in accordance with BS EN 322
 - 10.1.9 Swelling due to water submersion in accordance with BS EN 317
 - 10.1.10 Fade resistance in accordance with Q-Lab Technical Bulletin LL-9025
 - 10.1.11 Stain resistance in accordance with BS EN 438-2
- 10.2 Information contained herein may include the result of testing and/or data analysis by sources that are <u>approved agencies</u>, <u>approved sources</u>, and/or an <u>RDP</u>. Accuracy of external test data and resulting analysis is relied upon.
- 10.3 Where applicable, testing and/or engineering analysis are based upon provisions that have been codified into law through state or local adoption of regulations and standards. The developers of these regulations and standards are responsible for the reliability of published content. DrJ's engineering practice may use a regulation-adopted provision as the control. A regulation-endorsed control versus a simulation of the conditions of application to occur establishes a new material as <u>being equivalent</u> to the regulatory provision in terms of quality, <u>strength</u>, effectiveness, <u>fire resistance</u>, durability, and safety.
- 10.4 The accuracy of the provisions provided herein may be reliant upon the published properties of raw materials, which are defined by the grade mark, grade stamp, mill certificate, or <u>duly authenticated reports</u> from <u>approved</u> <u>agencies</u> and/or <u>approved sources</u> provided by the supplier. These are presumed to be minimum properties and relied upon to be accurate. The reliability of DrJ's engineering practice, as contained in this <u>duly</u> <u>authenticated report</u>, may be dependent upon published design properties by others.
- 10.5 Testing and Engineering Analysis:
 - 10.5.1 The strength, rigidity, and/or general performance of component parts and/or the integrated structure are determined by suitable tests that simulate the actual conditions of application that occur and/or by accepted engineering practice and experience.³⁶
- 10.6 Where additional condition of use and/or regulatory compliance information is required, please search for Millboard Composite Siding on the <u>DrJ Certification website</u>.





11 Findings

- 11.1 As outlined in **Section 6**, Millboard Composite Sidings have performance characteristics that were tested and/or meet applicable regulations. In addition, they are suitable for use pursuant to its specified purpose.
- 11.2 When used and installed in accordance with this <u>duly authenticated report</u> and the manufacturer installation instructions, Millboard Composite Siding shall be approved for the following applications:
 - 11.2.1 Used as an exterior wall covering to provide a weather-resistive barrier.
 - 11.2.2 Use as external siding on buildings in accordance with <u>IBC Section 1403.8</u> and <u>IRC Section R703</u>.
 - 11.2.3 Millboard Composite Siding products were evaluated for installation as part of a rainscreen system.
 - 11.2.3.1 Millboard Composite Sidings are installed onto furring strips or nailbase with a ¹/₄" thick rainscreen mesh in between siding and substrate.
 - 11.2.3.2 Fasteners specified in this report are capable of sustaining the dead load of Millboard Composite Sidings.
 - 11.2.4 Furring strips/nailbase in conjunction with a rainscreen mesh provides an air pocket to facilitate drainage behind Millboard Composite Sidings. Limitations are listed in **Section 12**.
- 11.3 Unless exempt by state statute, when Millboard Composite Sidings are to be used as a structural and/or building envelope component in the design of a specific building, the design shall be performed by an <u>RDP</u>.
- 11.4 Any application specific issues not addressed herein can be engineered by an <u>RDP</u>. Assistance with engineering is available from Millboard Company, Ltd.
- 11.5 IBC Section 104.2.3³⁷ (IRC Section R104.2.2³⁸ and IFC Section 104.2.3³⁹ are similar) in pertinent part state:

104.2.3 Alternative Materials, Design and Methods of Construction and Equipment. The provisions of this code are not intended to prevent the installation of any material or to prohibit any design or method of construction not specifically prescribed by this code, provided that any such alternative is not specifically prohibited by this code and has been approved.

- 11.6 Approved:⁴⁰ Building regulations require that the building official shall accept duly authenticated reports.⁴¹
 - 11.6.1 An approved agency is "approved" when it is ANAB ISO/IEC 17065 accredited.
 - 11.6.2 An <u>approved source</u> is *"approved"* when an <u>RDP</u> is properly licensed to transact engineering commerce.
 - 11.6.3 Federal law, <u>Title 18 US Code Section 242</u>, requires that, where the alternative product, material, service, design, assembly, and/or method of construction is not approved, the building official shall respond in writing, stating the reasons why the alternative was not approved. Denial without written reason deprives a protected right to free and fair competition in the marketplace.
- 11.7 DrJ is a licensed engineering company, employs licensed <u>RDP</u>s and is an <u>ANAB Accredited Product</u> <u>Certification Body – Accreditation #1131</u>.
- 11.8 Through the <u>IAF Multilateral Arrangement</u> (MLA), this <u>duly authenticated report</u> can be used to obtain product approval in any <u>jurisdiction</u> or <u>country</u> because all ANAB ISO/IEC 17065 <u>duly authenticated reports</u> are equivalent.⁴²





12 Conditions of Use

- 12.1 Material properties shall not fall outside the boundaries defined in **Section 6**.
- 12.2 As defined in **Section 6**, where material and/or engineering mechanics properties are created for load resisting design purposes, the resistance to the applied load shall not exceed the ability of the defined properties to resist those loads using the principles of accepted engineering practice.
- 12.3 Millboard Composite Sidings (Shadow Line+ and Board & Batten+) shall be installed over a structural wall assembly capable of withstanding the imposed positive and negative design loads.
 - 12.3.1 Exterior walls shall be braced or sheathed with approved materials to resist lateral loads.
 - 12.3.2 The exterior sheathing substrate shall be fastened to wall framing members in accordance with the applicable building codes.
 - 12.3.2.1 An approved Water-Resistive Barrier (WRB) shall be secured on top of the exterior sheathing where required by the applicable building codes.
 - 12.3.2.2 Flashing in accordance with the applicable code shall be installed at all openings, penetrations, abutting components, and at terminations of siding and soffit to ensure weather-tightness of the assembly.
 - 12.3.3 Building code provisions for the fasteners used to secure Millboard Composite Sidings to furring or nailbase shall be followed.
 - 12.3.3.1 Connections between furring or nailbase to structural wall assembly is not in the scope of this report.
 - 12.4 As listed herein, Millboard Composite Sidings shall not be used:
 - 12.4.1 As the primary wall bracing system
 - 12.4.2 On the interior face of walls
 - 12.4.3 As part of a fire-rated assembly
 - 12.4.4 In Types I through IV construction
 - 12.4.5 Where design wind pressure exceeds the allowable wind loads as permitted in Table 2 through Table 5
 - 12.4.6 Without the installation of a WRB between the sheathing and the siding products
 - 12.5 When required by adopted legislation and enforced by the <u>building official</u>, also known as the Authority Having Jurisdiction (AHJ) in which the project is to be constructed:
 - 12.5.1 Any calculations incorporated into the construction documents shall conform to accepted engineering practice and, when prepared by an <u>approved source</u>, shall be approved when signed and sealed.
 - 12.5.2 This report and the installation instructions shall be submitted at the time of <u>permit</u> application.
 - 12.5.3 These innovative products have an internal quality control program and a third-party quality assurance program.
 - 12.5.4 At a minimum, these innovative products shall be installed per Section 9.
 - 12.5.5 The review of this report by the AHJ shall comply with <u>IBC Section 104.2.3.2</u> and <u>IBC Section 105.3.1</u>.
 - 12.5.6 These innovative products have an internal quality control program and a third party quality assurance program in accordance with <u>IBC Section 104.7.2</u>, <u>IBC Section 110.4</u>, <u>IBC Section 1703</u>, <u>IRC Section R109.2</u>.
 - 12.5.7 The application of these innovative products in the context of this report is dependent upon the accuracy of the construction documents, implementation of installation instructions, inspection as required by <u>IBC</u> <u>Section 110.3</u>, <u>IRC Section R109.2</u>, and any other regulatory requirements that may apply.





- 12.6 The approval of this report by the AHJ shall comply with <u>IBC Section 1707.1</u>, where legislation states in part, *"the <u>building official</u> shall make, or cause to be made, the necessary tests and investigations; or the <u>building</u> <u>official</u> shall accept duly authenticated reports from <u>approved agencies</u> in respect to the quality and manner of use of new materials or assemblies as provided for in <u>Section 104.2.3</u>", all of <u>IBC Section 104</u>, and <u>IBC Section 105.3</u>.*
- 12.7 <u>Design loads</u> shall be determined in accordance with the regulations adopted by the jurisdiction in which the project is to be constructed and/or by the building designer (i.e., <u>owner</u> or <u>RDP</u>).
- 12.8 The actual design, suitability, and use of this report for any particular building, is the responsibility of the owner or the authorized agent of the <u>owner</u>.

13 Identification

- 13.1 The innovative products listed in **Section 1.1** are identified by a label on the board or packaging material bearing the manufacturer name, product name, this report number, and other information to confirm code compliance.
- 13.2 Additional technical information can be found at <u>www.millboard.com</u>.

14 Review Schedule

- 14.1 This report is subject to periodic review and revision. For the latest version, visit <u>www.drjcertification.org</u>.
- 14.2 For information on the status of this report, please contact DrJ Certification.





Issue Date: March 27, 2025 Subject to Renewal: July 1, 2026

FBC Supplement to Report Number 2304-117

REPORT HOLDER: Millboard® Company, Ltd.

1 Evaluation Subject

- 1.1 Millboard Composite Siding:
 - 1.1.1 Shadow Line+
 - 1.1.2 Board & Batten+

2 Purpose and Scope

- 2.1 Purpose
 - 2.1.1 The purpose of this Report Supplement is to show Millboard Composite Sidings, recognized in Report Number 2304-117, have also been evaluated for compliance with the codes listed below as adopted by the Florida Building Commission.
- 2.2 Applicable Code Editions
 - 2.2.1 FBC-B—20, 23: Florida Building Code Building (FL 47417)
 - 2.2.2 FBC-R—20, 23: Florida Building Code Residential (FL 47417)

3 Conclusions

- 3.1 Millboard Composite Sidings, described in Report Number 2304-117, comply with the FBC-B and FBC-R and are subject to the conditions of use described in this supplement.
 - 3.1.1 Where there are variations between the IBC and IRC and the FBC-B and FBC-R applicable to this report, they are listed here:
 - 3.1.1.1 FBC-B Section 104 is reserved.
 - 3.1.1.2 FBC-B Section 110.4 is reserved and replaces IBC Section 110.4.
 - 3.1.1.3 FBC-B Section 104.6 is reserved and replaces IBC Section 104.4.
 - 3.1.1.4 FBC-B Section 104.11 replaces IBC Section 104.2.3 and Section 104.2.3.2.
 - 3.1.1.5 FBC-B Section 105.3 replaces IBC Section 105.3.
 - 3.1.1.6 FBC-B Section 105.3.1 replaces IBC Section 105.3.1.
 - 3.1.1.7 FBC-B Section 110.3 replaces IBC Section 110.3.
 - 3.1.1.8 FBC-B Section 1403 replaces IBC Section 1402.
 - 3.1.1.9 FBC-B Section 1403.5 replaces IBC Section 1403.2.
 - 3.1.1.10 FBC-B Section 1404.9 replaces IBC Section 1403.8.
 - 3.1.1.11 FBC-B Section 1707.1 replaces IBC Section 1707.1.
 - 3.1.1.12 FBC-B Section 2304.12 replaces IBC Section 2304.12.
 - 3.1.1.13 FBC-B Section 2306.1 replaces IBC Section 2306.1.
 - 3.1.1.14 FBC-B Section 2306.3 replaces IBC Section 2306.3.





- 3.1.1.15 FBC-R Section R104 and Section R109 are reserved.
- 3.1.1.16 FBC-R Section R301.2.1 replaces IRC Section R301.2.1.
- 3.1.1.17 FBC-R Section R317 replaces IRC Section R304.
- 3.1.1.18 FBC-R Section R318 replaces IRC Section R305.
- 3.1.1.19 FBC-R Section R703.1.1 replaces IRC Section R703.1.1.
- 3.1.1.20 FBC-R Section R703.1.2 replaces IRC Section R703.1.2.

4 Conditions of Use

- 4.1 Millboard Composite Siding, described in Report Number 2304-117, must comply with all of the following conditions:
 - 4.1.1 For use in HVHZ, Millboard Composite Sidings must be installed with a ⁵/₈" plywood backer or equivalent backer.
 - 4.1.2 All applicable sections in Report Number 2304-117.
 - 4.1.3 The design, installation, and inspections are in accordance with additional requirements of FBC-B Chapter 16 and Chapter 17, as applicable.





Notes

- ¹ For more information, visit <u>dricertification.org</u> or call us at 608-310-6748.
- ² Capitalized terms and responsibilities are defined pursuant to the applicable building code, applicable reference standards, the latest edition of <u>TPI1</u>, the <u>NDS</u>, <u>AISI S202</u>, <u>US</u> professional engineering law, <u>Canadian building code</u>, <u>Canada professional engineering law</u>, <u>Qualtim External Appendix A: Definitions/Commentary</u>, <u>Qualtim External Appendix B:</u> <u>Project/Deliverables</u>, <u>Qualtim External Appendix C: Intellectual Property and Trade Secrets</u>, definitions created within Design Drawings and/or definitions within Reference Sheets. Beyond this, terms not defined shall have ordinarily accepted meanings as the context implies. Words used in the present tense include the future; words stated in the masculine gender include the feminine and neuter; the singular number includes the plural and the plural, the singular.
- ³ https://up.codes/viewer/mississippi/ibc-2024/chapter/17/special-inspections-and-tests#1702
- ⁴ Alternative Materials, Design and Methods of Construction and Equipment: The provisions of any regulation code are not intended to prevent the installation of any material or to prohibit any design or method of construction not specifically prescribed by a regulation. Please review <u>https://www.justice.gov/atr/mission</u> and https://up.codes/viewer/mississippi/ibc-2024/chapter/1/scope-and-administration#104.2.3
- 5 <u>https://up.codes/viewer/mississippi/ibc-2024/chapter/17/special-inspections-and-tests#1706.2:~:text=the%20design%20strengths%20and%20permissible%20stresses%20shall%20be%20established%20by%20tests</u>
- 7 https://up.codes/viewer/mississippi/ibc-2024/chapter/17/special-inspections-andtests#1707.1;~:text=the%20building%20official%20shall%20make%2C%20or%20cause%20to%20be%20made%2C%20the%20necessary%20tests%20and%20investigations%3B %20or%20the%20building%20official%20shall%20accept%20duly%20authenticated%20reports%20from%20approved%20agencies%20in%20respect%20to%20the%20quality%2 0and%20manner%20of%20use%20of%20new%20materials%20or%20assemblies%20as%20provided%20for%20in%20Section%20104.2.3.
- 8 https://up.codes/viewer/mississippi/ibc-2024/chapter/17/special-inspections-and-tests#1703.4.2
- 9 https://up.codes/viewer/mississippi/ibc-2024/chapter/2/definitions#approved_agency
- ¹⁰ https://up.codes/viewer/mississippi/ibc-2024/chapter/2/definitions#approved_source
- https://www.law.cornell.edu/uscode/text/18/1832 (b) Any organization that commits any offense described in subsection (a) shall be fined not more than the greater of \$5,000,000 or 3 times the value of the stolen trade secret to the organization, including expenses for research and design and other costs of reproducing the trade secret that the organization has thereby avoided. The <u>federal government</u> and each state have a <u>public records act</u>. To follow DTSA and comply state public records and trade secret legislation requires approval through <u>ANAB ISO/IEC 17065 accredited certification bodies</u> or <u>approved sources</u>. For more information, please review this website: <u>Intellectual Property and Trade Secrets</u>.
- 12 <u>https://www.nspe.org/resources/issues-and-advocacy/professional-policies-and-position-statements/regulation-professional AND https://apassociation.org/list-of-engineeringboards-in-each-state-archive/</u>
- 13 https://www.cbitest.com/accreditation/
- 14 https://up.codes/viewer/mississippi/ibc-2024/chapter/1/scope-and-administration#104.1:~:text=directed%20to%20enforce%20the%20provisions%20of%20this%20code
- ¹⁵ <u>https://up.codes/viewer/mississippi/ibc-2024/chapter/1/scope-and-administration#104.2.3</u> AND <u>https://up.codes/viewer/mississippi/ibc-2024/chapter/1/scope-and-administration#105.3.1</u>
- ¹⁶ <u>https://up.codes/viewer/mississippi/ibc-2024/chapter/17/special-inspections-and-tests#1707.1</u>
- https://iaf.nu/en/about-iafmla/#:~:text=Once%20an%20accreditation%20body%20is%20a%20signatory%20of%20the%20IAF%20MLA%2C%20it%20is%20required%20to%20recognise%20certificates%20 and%20validation%20and%20verification%20statements%20issued%20by%20conformity%20assessment%20bodies%20accredited%20by%20all%20other%20signatories%20of %20the%20IAF%20MLA%2C%20with%20the%20appropriate%20scope
- ¹⁸ True for all ANAB accredited product evaluation agencies and all International Trade Agreements.
- ¹⁹ <u>https://www.justice.gov/crt/deprivation-rights-under-color-law</u> AND <u>https://www.justice.gov/atr/mission</u>
- ²⁰ Unless otherwise noted, the links referenced herein use un-amended versions of the <u>2024 International Code Council (ICC)</u> 2024 International Code Council (ICC) model codes as foundation references. Mississippi versions of the <u>IBC 2024</u> and the <u>IRC 2024</u> are un-amended. This material, product, design, service and/or method of construction also complies with the 2000-2012 versions of the referenced codes and the standards referenced therein. As pertinent to this technical and code compliance evaluation, CBI and/or DrJ staff have reviewed any state or local regulatory amendments to assure this report is in compliance.
- ²¹ See <u>Adoptions by Publisher</u> for the latest adoption of a non-amended or amended model code by the local jurisdiction. <u>https://up.codes/codes/general</u>
- ²² See <u>Adoptions by Publisher</u> for the latest adoption of a non-amended or amended model code by state. <u>https://up.codes/codes/general</u>
- ²³ https://www.ecfr.gov/current/title-24/subtitle-B/chapter-XX/part-3282/subpart-A/section-3282.14
- ²⁴ <u>https://www.ecfr.gov/current/title-24/subtitle-B/chapter-XX/part-3280</u>
- ²⁵ All references to the FBC-B and FBC-R are the same as the 2024 IBC and 2024 IRC unless otherwise noted in the Florida Supplement at the end of this report.
- ²⁶ <u>https://www.ecfr.gov/current/title-24/subtitle-B/chapter-XX/part-3280#p-3280.2(Listed%20or%20certified); https://up.codes/viewer/mississippi/ibc-2024/chapter/2/definitions#listed AND https://up.codes/viewer/mississippi/ibc-2024/chapter/2/definitions#labeled</u>
- 27 2021 IRC Section R317
- 28 2021 IRC Section R318
- ²⁹ https://up.codes/viewer/mississippi/ibc-2024/chapter/17/special-inspections-and-tests#1703.4
- 30 https://www.ecfr.gov/current/title-24/subtitle-B/chapter-XX/part-
- 3280#:~:text=All%20construction%20methods%20shall%20be%20in%20conformance%20with%20accepted%20engineering%20practices%20to%20insure%20durable%2C%20liv able%2C%20and%20safe%20housing%20and%20shall%20demonstrate%20acceptable%20workmanship%20reflecting%20journeyman%20quality%20of%20work%20of%20the% 20various%20trades





³¹ <u>https://www.ecfr.gov/current/title-24/subtitle-B/chapter-XX/part-</u>

3280#:~:text=The%20strength%20and%20rigidity%20of%20the%20component%20parts%20and/or%20the%20integrated%20structure%20shall%20be%20determined%20by%20 engineering%20analysis%20or%20by%20suitable%20load%20tests%20to%20simulate%20the%20actual%20loads%20and%20conditions%20of%20application%20that%20occur

- ³² 2015 IBC Section 1403
- ³³ 2015 IBC Section 1404.2
- ³⁴ Qualification is performed by a legislatively defined <u>Accreditation Body</u>. <u>ANSI National Accreditation Board (ANAB)</u> is the largest independent accreditation body in North America and provides services in more than 75 countries. <u>DrJ</u> is an ANAB accredited <u>product certification body</u>.
- ³⁵ <u>https://anabpd.ansi.org/Accreditation/product-certification/AllDirectoryDetails?prgID=1&orgID=2125&statusID=4#:~:text=Bill%20Payment%20Date-,Accredited%20Scopes.-13%20ENVIRONMENT.%20HEALTH</u>
- 36 See Code of Federal Regulations (CFR) Title 24 Subtitle B Chapter XX Part 3280 for definition: https://www.ecfr.gov/current/title-24/subtitle-B/chapter-XX/part-3280
- ³⁷ 2021 IBC Section 104.11
- ³⁸ 2021 IRC Section R104.11
- ³⁹ 2018: <u>https://up.codes/viewer/wyoming/ifc-2018/chapter/1/scope-and-administration#104.9</u> AND 2021: <u>https://up.codes/viewer/wyoming/ibc-2021/chapter/1/scope-and-administration#104.11</u>
- ⁴⁰ Approved is an adjective that modifies the noun after it. For example, Approved Agency means that the Agency is accepted officially as being suitable in a particular situation. This example conforms to IBC/IRC/IFC Section 201.4 (<u>https://up.codes/viewer/mississippi/ibc-2024/chapter/2/definitions#201.4</u>) where the building code authorizes sentences to have an ordinarily accepted meaning such as the context implies.
- ⁴¹ <u>https://up.codes/viewer/mississippi/ibc-2024/chapter/17/special-inspections-and-tests#1707.1</u>
- ⁴² Multilateral approval is true for all ANAB accredited product evaluation agencies and all International Trade Agreements.